



LINE-UP[®] WATER-BASED PAVEMENT STRIPING PAINT

K4113 Series

Krylon[®] Industrial Line-Up[®] Pavement Striping Paint is a water-based liquid product for use on blacktop, concrete, curbs or other smooth, hard surfaces.

- ✓ Fast drying
- ✓ Excellent bleed retention
- ✓ One coat coverage
- ✓ Conforms with U.S. Bureau of Public Roads colors

INDUSTRIAL USE ONLY! AS OF 01/01/2017 COMPLIES WITH:

- ✓ OTC
- ✓ EC
- ✓ SCAQMD
- ✓ CARB
- ✓ LADCO
- ✓ UTAH

krylonindustrial.com
1-800-247-3266

Revised December 2017

SURFACE PREPARATION

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull or scrubbed with an abrasive cleaner. Surface should be clean and dry and free from loose or peeling paint. Do not apply when air or surface temperatures are below 50 F, or when the relative humidity exceeds 85%, or when the temperature falls below the dew point. The presence of concrete sealers or efflorescence on new concrete may interfere with adhesion and should be removed by extended weathering, etching, or abrasive blasting. Most previously painted lines may be repainted without additional surface preparation, provided the old paint is still tightly adhered to the surface. However, multiple layers of paint will eventually peel and require removal. New asphalt surfaces should ideally be allowed to age several months before striping. Latex paint will not bleed on most asphalt, but shrinkage of the paint film during curing can cause new asphalt to lift or crack. Exceeding the recommended film thickness will increase the tendency to cause asphalt lifting. Placing an inconspicuous test stripe to determine if a new asphalt surface has cured sufficiently to paint is recommended.

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

APPLICATION

Do not paint on wet surfaces or when humidity is above 85% or when air or surface temperatures are below 50 F or when temperature falls below the dew point. For **brush** application, no reduction is necessary. Use a nylon/polyester brush. For **roller** application, no reduction is necessary. Use appropriate synthetic nap size roller cover. For **airless spray** thinning not recommended. If necessary, thin with up to 1 pint per gallon of water. Use .015" - .017" Tip, 50 - 100 mesh filter and 1,800 to 2,700 psi fluid pressure. For conventional spray not recommended.

TECHNICAL DATA

Finish:	Flat
Color:	1 gal, 5 gal
Drying Time:	To Touch: 30 minutes No traffic pick up after 60 minutes.
Rec. Spread Rate:	(calculated) 15 gals. per mile of standard 4" strip or 350 lineal ft. of standard 4" strip per gal. (New) 15 mils wet, 7 mils dry. (Existing) 10 mils wet, 5 mils dry.
Vehicle Type:	100% Acrylic
Flash Point:	102 F PM Closed Cup
VOC:	<95 g/L, 0.79 lb/gal
Clean Up:	Soap and Water

CAUTION

Thoroughly review product label and SDS for safety and cautions prior to using this product. Please direct any questions or comments to your local Krylon Industrial Representative.

Note: The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer handling and methods of application which are not known or under our control, Krylon Products Group cannot make any warranties as to the end result. Please direct any questions or comments to 1-800-247-3266.



krylonindustrial.com
1-800-247-3266

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of Krylon Industrial. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Krylon Industrial dealer or representative to obtain the most recent Product Data Sheet.