



ALKYD HARDNER

Alkyd Hardener is intended for use in Tough Coat® Quik-Dry™ Alkyd Enamel. Used properly, Alkyd Hardener will significantly enhance the performance properties of Tough Coat Quik-Dry. Expected results should be increased chemical/abrasion resistance, improved hardness plus sharper gloss and better color and gloss retention.

- ✓ Increased chemical and abrasion resistance
- ✓ Improved hardness, gloss and color retention

INDUSTRIAL USE ONLY! AS OF 01/01/16 COMPLIES WITH:

- OTC
- EC
- SCAQMD
- CARB
- LADCO

krylonindustrial.com
1-800-247-3266

Revised June 2016

TECHNICAL DATA

Finish	Gloss Enhancer
Volume Solids	69.8%
Weight Solids	75.0%
VOC	2.2 lbs./gal. (265 g/l)
Package Life	12 months
Packaging	Available in quart containers
Drying Time	
	Note: Tough Coat Quik-Dry must be catalyzed at an 8:1 ratio (1 pint per gallon) with Alkyd Hardener prior to reduction. With the induction of Alkyd Hardener, dry times will be slower than Tough Coat Quik-Dry uncatalyzed and are as follows:
To Touch:	15 - 20 minutes
To Handle:	40 - 60 minutes
To Tape:	60 - 90 minutes
To Recoat	After 60 minutes
To Pack	24 hours
Pot Life	6 - 8 Hours
Sweat In Time	15 minutes @ 77°F (must be mixed well)

PRECAUTIONS

Alkyd Hardener must be protected from contamination, especially with moisture. Moisture will react with the catalyst, thereby decreasing its effectiveness, which may lead to incomplete curing of the paint film.

DANGER: CONTAINS ISOCYANATE. PREPOLYMER MAY CAUSE LUNG IRRITATION AND ALLERGIC RESPIRATORY REACTION, VAPOR HARMFUL. USE ONLY WITH ADEQUATE VENTILATION.

If engineering and administrative controls of contaminants are not feasible, wear a vapor/particulate respirator (W.S. Bureau of Mines BE-23 and NIOSH 23C or equivalent) during application and until work area has been exhausted of all vapor and spray mist. Individuals with chronic respiratory problems or prior respiratory reactions to isocyanate MUST NOT BE EXPOSED to vapors or spray mist, remove to fresh air. If breathing difficulty persists or occurs later, consult a physician and have label information available. May Irritate Skin and Eyes. Avoid contact with eyes and skin. In case of eye contact, flush immediately with plenty of water for 15 minutes; CALL A PHYSICIAN. In case of skin contact wash thoroughly with soap and water.

CAUTIONS

FOR INDUSTRIAL USE ONLY. Thoroughly review product label and SDS for safety and cautions prior to using this product. Please direct any questions or comments to your local Krylon Industrial Representative.

Note: The information, rating, and opinions stated here pertain to the material currently offered and represent the results of tests believed to be reliable. However, due to variations in customer

handling and methods of application which are not known or under our control, Krylon Products Group cannot make any warranties as to the end result. Please direct any questions or comments to 1-800-247-3266.