

Minwax® Technical Data Sheet
MINWAX® Hardwood Floor Reviver- Low Gloss, High Gloss



DESCRIPTION:

Minwax® Hardwood Floor Reviver quickly and easily renews the beauty of hardwood floors that are dull, scratched, or show signs of wear. Stronger and more durable than polish, Reviver is a topcoat that restores shine and provides a layer of protection to any unwaxed, polyurethane-finished floor.

RECOMMENDED USE:

Minwax® Hardwood Floor Reviver is recommended for use on unwaxed, polyurethane-finished floors that have not been polished or oiled.

NOTE: To test for wax, apply a few drops of water to the floor. Wait 10 minutes. If the wetted area turns white, the floor may have a wax coating. Reviver is not designed for use on floors that are in very poor condition. Badly damaged floors or floors that have large areas where the finish is worn away will require a complete refinishing.

SURFACE PREPARATION:

- Ensure that the floor is free of old finishes in poor condition, wax, grease, polish, dirt, or other foreign matter.
- Vacuum floor thoroughly and clean with Minwax® Hardwood Floor Cleaner or other mild cleaner.
- Allow floor to dry before applying Minwax® Hardwood Floor Reviver.
- Test Reviver on a small inconspicuous area of the floor, such as inside a closet, to ensure adhesion and compatibility. Wax and other ingredients in some floor polishes may cause Reviver to bead up or prevent it from adhering to the floor properly.

APPLICATION NOTES:

- 1) Rock the bottle several times before opening the cap. Do not shake.
- 2) Squirt Minwax® Hardwood Floor Reviver lightly in an "S" pattern directly onto the floor in a 3 x 3 foot area.
- 3) Using a damp painter's pad or synthetic applicator attached to a long handle, spread Reviver across the floor. Work in the direction of the grain using a back-and-forth motion.
- 4) Keep working in small sections until the entire floor is coated. For best results, apply a thin, even coat. Keep airborne dust to a minimum while the floor is wet.
- 5) Allow coating to dry.

NOTE: Thinning is not recommended. Hardwood Floor Reviver is for interior use only.

PRECAUTIONS:

Minwax® Hardwood Floor Reviver is not recommended for use over stain or unfinished wood. Use with adequate ventilation.

DRY TIME:

- Let the finish dry at least two hours before walking lightly on the floor. Do not walk on the floor if surface is wet or tacky. Avoid heavy traffic and do not replace furniture or rugs for 24 hours after application. When replacing furniture, do not slide.
- Dry times are based on conditions of 77°F and 50% relative humidity. Thicker applications than recommended, lower temperature, and higher humidity will extend dry time. Do not apply at temperatures under 50°F or at very high humidity.

MAINTENANCE:

To clean surfaces protected with Minwax® Hardwood Floor Reviver, damp wiping with a gentle cleaner such as Minwax® Hardwood Floor Cleaner is recommended. Minwax® Hardwood Floor Reviver can be reapplied as needed (usually about every 6 months) to keep your floor looking beautiful.

CLEANUP/STORAGE:

Keep from freezing. Store below 105°F. Clean applicator immediately after use with warm water. Application tools can be cleaned with soap and water.

SAFETY:

CAUTIONS: Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call the Poison Control Center, hospital emergency room, or physician immediately. **WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.** Max. VOC 275 g/L (2.3 lbs. /gal) Do not thin. Nonphotochemically reactive.

PHYSICAL PROPERTIES:

Resin type:	Acrylic. Polyurethane
Solvent:	Water. Glycol ethers
Luster:	High GlossLow Gloss85 Minimum57 +/- 5
No. of coats:	1 recommended
Dry-time:	2 hours light traffic; 24 hours normal use
Dry film thickness:	0.5 mil/coat
Flash point:	> 200°F
Applicator:	High quality synthetic applicator
VQC (grams/liter):	275 Maximum
Coverage (sq. ft./qt.):	175-225
% Solids:	24- 26
Pounds/gallon:	8.38- 8.60
Viscosity (centipose):	80-120