

MINWAX® Technical Data Sheet
MINWAX® PASTE FINISHING WAX

DESCRIPTION:

Protects and adds luster to any stained wood surfaces.

RECOMMENDED USE:

Designed for interior use on stained wood surfaces that do not need the hard protective coat of polyurethane.

SURFACE PREPARATION:

The stained wood surface should be dry and clean.

APPLICATION NOTES:

1. Apply a thin, even coat of wax with a clean cloth.
2. Allow wax to dry thoroughly (10-15 minutes) then polish.
3. For a deeper luster, apply a second coat.

• Read all label directions and cautions carefully before use *

PRECAUTIONS:

Surface must be dry before application. Apply after 24 hours to newly stained wood surfaces.

MAINTENANCE:

To maintain the Paste Finish, lightly buff after removing the dirt with a slightly dampened cloth and mild detergent.

CLEANUP/STORAGE:

Do not store near hear, sparks, open flames or other sources of ignition. Close container after each use. Store only in original container.

SAFETY:

DANGER: HARMFUL OR FATAL IF SWALLOWED. SKIN IRRITANT. COMBUSTIBLE. KEEP OUT OF REACH OF CHILDREN.

CAUTION: COMBUSTIBLE MIXTURE N.Y.F.D.C. of A. No. 1187. **DANGER: KEEP OUT OF REACH OF CHILDREN.** Contains mineral spirits. Do not take internally. Avoid contact with skin and eyes. Use with adequate ventilation. Provide a constant flow of fresh air. Keep away from heat, sparks, open flame or other sources of ignition. Close container after each use. **FIRST AID: IF SWALLOWED:** Do not induce vomiting. Call physician immediately. **FOR SKIN CONTACT:** Wash thoroughly with soap and water. If irritation persists, get medical attention. **FOR EYE CONTACT: IMMEDIATELY** flush eyes thoroughly with water, then remove any contact lenses. Continue to flush eyes with water for at least 15 minutes. If irritation persists, get medical attention. **IF AFFECTED BY INHALATION:** Immediately remove to fresh air. If symptoms

PHYSICAL PROPERTIES:

Testing method:

Resin type:	Blend of natural and synthetic waxes	
Solvent:	Mineral spirits	
Odor:	Mild hydrocarbon	
No. of coats:	1 or 2	
Coverage:	500 sq. ft./lb.	
Flash point:	>104 Fahrenheit	SETAFLASH*
% Solids:	29.637 +/- .50	ASTM D 2369-86
Specific gravity:	.814 +/- .005	ASTM D 1475-85
Applicator:	Cheesecloth	

*SETAFLASH is a registered trademark of Stanhope-Seta Limited.