

Technical Data Sheet

- PUL MP RAGGRINZATI serie 319

GENERAL FEATURES

Thermosetting powder with epoxy and polyester resins.

APPLICATION

Due to its special content the product has excellent protective and decorative effects. It is suggested particularly for interior coating.

ADVISED CYCLES

The surface to be coated must be cleaned from oils, grease or flash rust.

If particular resistance to corrosion or humidity is required, it is suggested the following pretreatment of the surface:

for steel	sand blasting or/and iron or zinc phosphatising
for galvanised steel and aluminium	chromatising

HANDLING AND STORAGE

Store at temperatures lower than 30°C; higher temperatures may damage the powder by causing undesired alterations or blobs.

Storage life in original package: 18 months.

TECHNICAL DATA

Code	Int. Method	Range	Ref. Method
P/CL092	Calc. specific gravity(kg/l):	1.25 - 1.650	
P/YC060	Particle size dist. <32µm (%):	36 - 46	
P/YC120	Particle size dist. <63µm (%):	74 - 91	
P/CL143	1µm Theor. spread.rate (m2/kg):	540 - 780	

WAYS OF APPLICATION

Apply with automatic or manual guns with negative terminal (60/80KV).

It is advised to apply in layers with the thickness of 60-80 microns and to stove at 200°C for 10 minutes.

For stoving of the epoxy polyester fine texture products it is possible to use the following combinations of time and temperature:

10-15 minutes	200°C (temperature of the support)
15-22 minutes	190°C (temperature of the support)
20-30 minutes	180°C (temperature of the support)

For stoving use the given indications.

TECHNOLOGICAL FEATURES AND RESISTANCE TESTS

The support used	non treated steel
Thickness	60 microns
Stoving	10 minutes at 200°C

The hardness test was carried out on zinc phosphatised steel.

Code	Int. Method	Range	Ref. Method
P/CM040	Erichsen cupping test (mm):	more than 3	UNI EN ISO 1520
P/CM050	Direct impact test (cm.Kg):	more than 20	ASTM D 2794; ISO 6272-2:2002
P/CM051	Reverse impact test(cm.kg):	more than 5	ASTM D 2794; ISO 6272-2:2002
P/CM170	Conical mandrel : Bend test	maximum 20 mm	UNI EN ISO 6860
P/CM100	Crosscut adhesion (2mm)(GT):	00	UNI EN ISO 2409

Rev. Date 28/5/2019 Page n. 1 of 2

INVER SpA con Unico Socio

Via di Corticella, 205 - 40128 Bologna (BO) - ITALY
Manufacturing and R&D Labs: Via Marconi 10/A - 40061 Minerbio (BO) ITALY
Ph. +39 051 638 0411 - www.inver.com - inver@sherwin.com
Inver SpA is a member of The Sherwin-Williams Company

SHERWIN-WILLIAMS

Technical Data Sheet

- PUL MP RAGGRINZATI serie 319

P/CM190	Salt fog test	:	1000 hours later - indentation along the cross of 3-6 mm	UNI ISO 9227
P/CM230	Resistance to humidity	:(Humidity test)	500 hours later - no change	UNI EN ISO 6270-2:2005

NOTE TO USER

The information contained in this document while based on evidence and reliable methods can not be considered exhaustive.

This information are current to the date of issuance of this data sheet, therefore is under user's responsibility to verify that the data provided on this sheet are current to the date of the product.

The user, under its own responsibility, shall respect all the existing provisions on hygiene and safety and shall verify every time the features and the specific and appropriate way to use the product, cause the respect of the provisions is not under producer's direct control.

The manufacturer does not guarantee nor assume any liability or responsibility for whatsoever harm that might result from a misuse of the product or for damages that have arisen after the product's distribution.