



# Valspar® Climate Zone Exterior Latex Satin Paint

## No. 27400 Series

### GENERAL DESCRIPTION

With only one coat, Valspar Climate Zone Exterior Latex Satin protects your home with a tough enamel coating that resists mildew and harsh weather. Warranted for 20 years, this fast drying flat fights fading, chalking and yellowing on exterior surfaces.

### PRODUCT FEATURES

- Resists fading, chalking & yellowing
- Gives mildew-resistant finish
- Dries quickly
- Easy soap & water cleanup
- Limited warranty

### RECOMMENDED USES

Properly prepared exterior surfaces including previously primed and painted wood siding and trim, hardboard siding, primed metal, shakes, shingles, brick, cement, cinder block, stucco, stone, asbestos, galvanized steel and aluminum siding. Do not use on glazed brick, glazed aluminum, glazed masonry, floors or steps.

### SHIPPING AND PACKAGING

**Freight Classification:** Paint or paint related material. Protect from freezing.

**Packaging:**

- Quart – 4 per carton
- Gallon – 4 per carton
- 5-gallon pail

### COMPOSITION

**Base and Fill Levels**  
(oz./gal.)

<b>White</b>	128
<b>Pastel Base (27405)</b>	126
<b>Tint Base (27410)</b>	124
<b>Clear Base (27429)</b>	116

### APPLICATION AND CLEANUP

Stir paint thoroughly before and during use. Use a premium quality roller or polyester brush. Paint gutters, window sashes and frames first. Then, start at the top of the house and work across, always ending up at a door, window or outer edge. May also be applied by airless sprayer, following the sprayer instructions. Note: To ensure uniform color, intermix all containers of the same color.

**Airless Spray:**

- Pressure: 2000 PSI
- Tip: 0.017–0.019"

**Brush:** premium-quality nylon or polyester brush

**Roller:** premium quality synthetic, 3/8" nap

### SYSTEM

### RECOMMENDATIONS

**New Wood:**

- Self-priming
- 2 Coats: Climate Zone Exterior Latex Satin Paint

**Previously Painted Surfaces:**

- Self-priming
- 1–2 Coats: Climate Zone Exterior Latex Satin Paint

**Hardboard Siding:**

- Self-priming
- 1–2 Coats: Climate Zone Exterior Latex Satin Paint

**Masonry, Concrete, Stucco, and Block:**

- Self-priming
- 1–2 Coats: Climate Zone Exterior Latex Satin Paint

**Metal:**

- 1 Coat: Appropriate metal primer
- 1–2 Coats: Climate Zone Exterior Latex Satin Paint

**Aluminum and Vinyl Siding:**

- Self-priming
- 1–2 Coats: Climate Zone Exterior Latex Satin Paint

### PRODUCT SPECIFICATIONS

**Vehicle Type:** Vinyl Acrylic & Acrylic Resins

**Viscosity:** 93-97 Krebs Units

**Flashpoint:** N/A

**VOC:** 150 g/L max 0.42 lb/gal as per 40 CFR 59.406

**Volume Solids:** 32%

**Weight Solids:** 43%

**Weight Per Gallon:** 10.1 lbs./gal.

**Practical Coverage:** Covers up to 400 sq. ft. per gallon (37 m<sup>2</sup> per 3.78 L) on smooth surfaces, 300 ft. on rough surfaces. Do not thin.

**Recommended Film Thickness:**

- 4.0 mil Wet
- 1.3 mil Dry

**Dry Time @ 77 °F and 50% Relative Humidity To The Touch:** 60 min.

**Recoat:** 4 hours

**Application Temperature:** 45–90 °F (2–32 °C)

### CERTIFICATIONS

Current as of: 9/13/2017

- MPI #
- MPI GPS 1
- MPI GPS 2
- LEED (US)
- LEED (Canada)

### REGULATORY COMPLIANCE

Current as of: 9/13/2017

- SCAQMD
- CARB 2000 SCM
- CARB 2007 SCM
- OTC/LADCO
- US National

### STORAGE AND DISPOSAL

Keep container closed when not in use. Do not transfer contents to other containers for storage or disposal. In case of spillage, absorb with inert material such as sand or kitty litter. Dispose of contaminated absorbent, container and/or unused contents in accordance with local, state and federal regulations. Do not freeze.

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information. UNLESS VALSPAR AGREES OTHERWISE IN WRITING, VALSPAR MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. VALSPAR WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.

